

Rittal – The System.

Faster – better – everywhere.



SV 3572.005 Laminated Copper Bar

State: 2025-12-17 (Source: [rittal.com/ca-en](https://www.rittal.com/ca-en))

ENCLOSURES

POWER DISTRIBUTION

CLIMATE CONTROL

IT INFRASTRUCTURE

SOFTWARE & SERVICES

FRIEDHELM LOH GROUP



SV 3572.005 - Laminated Copper Bar

Cu lamina made of high-purity electrolyte copper, length: 2000 mm/bar.



Features

Model No.	SV 3572.005
Material	Cu lamina: High-purity electrolyte copper Insulation: Highly resistant vinyl blend, expansion 370%, temperature: -30°C ... +105°C, fire protection according to UL-94 V0, dielectric strength: 20 kV/mm
Length	2,000 mm
Rated current for temperature increase 50 K	770 A
Rated current for temperature increase 30 K	585 A
Rated current for temperature increase 70 K	920 A

Features

Note	<p>Assembly = number of layers x layer width x layer thickness</p> <p>May be cut to length as required</p> <p>The conductor temperature of the laminated copper bar is derived by adding the ambient temperature and the temperature increase together. Example: 3565.005 carrying 180 A, i.e. the temperature increases by 30 K. At an ambient temperature of 35 °C, this produces a resultant conductor temperature of 35 °C + 30 K = 65 °C.</p>
Laminated flat copper version	<p>Number of lamina: 10</p> <p>Lamina width: 24 mm</p> <p>Lamina thickness: 1 mm</p>
Packaging unit	1 pc(s).
Net weight	4.813
Gross weight	4.94
Copper weight (kg per piece)	4.3
Customs tariff number	85446010
EAN	4028177666788
ETIM 9	EC001522
ETIM 8	EC001522
ECLASS 8.0	27370303

Approvals

Approvals	UR + C-UR (recognized)
Explanations	<p>Declaration of conformity</p> <p>Declaration of conformity UK</p>